

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

What is claimed is:

1. A recycling method for recycling a cake obtained by solidifying particles that are generated at a step of machining a crystal ingot to a wafer, or at a step of
5 machining a semiconductor wafer.

2. A recycling method according to claim 1, wherein said cake is obtained at a predetermined water content, without the occurrence of a chemical reaction.

3. A recycling method according to claim 1 or 2,
10 wherein said machining step is an abrading, grinding or polishing step.

4. A recycling method according to claim 1 or 2, wherein said step of machining said semiconductor wafer is a dicing, back grinding or wafer polishing step.

15 5. A recycling method according to one of claims 1 to 4, wherein said particles are Si flakes.

6. A recycling method for recycling, as a material to be melted or mixed, a cake that is obtained by solidifying particle generated at a step of machining a crystal ingot to
20 a wafer, or at a step of machining a semiconductor wafer.

7. A recycling method for employing as a material to be melted, a cake that is obtained by solidifying particle generated at a step of machining a crystal ingot to a wafer,

or at a step of machining a semiconductor wafer, and for recycling said cake as an ingot.

8. A recycling method for employing as a material to be melted, a cake that is obtained by solidifying, at a predetermined water content, particles generated at a step of machining a crystal ingot to a wafer, or at a step of machining a semiconductor wafer, and for recycling said cake as an ingot.

9. A method for fabricating a semiconductor ingot wherein a cake that is obtained by solidifying, at a predetermined water content and without a reaction with a chemical occurring, particles generated at a step of machining a crystal ingot to a wafer, or at a step of machining a semiconductor wafer, is employed as a material to be molted.

10. A recycling method according to one of claims 6 to 8, wherein said machining step is an abrading, grinding or polishing, dicing, back grinding or wafer polishing step.

11. A method according to claim 9, wherein said machining step is an abrading, grinding or polishing, dicing, back grinding or wafer polishing step.

12. A method for fabricating a semiconductor ingot comprising the steps of:

discharging, to a waste tank, not only water but also
Si particle generated at a step of machining a crystal ingot
to a wafer, or at a step of machining a semiconductor wafer;
adjusting waste water in said waste water tank to a
5 predetermined density by using a filter device;
transferring said waste water having said predetermined
density to collection means;
discharging said waste water under pressure;
using said collection means to generate a block that
10 consists of said Si particle at a predetermined water
content and that does not react with a chemical in said
waste water tank; and
using said block consisting of said Si particle as a
material to be melted for recycling.

15 13. A method according to claim 12, wherein water used
at said machining step contains carbon dioxide gas.

14. A method according to any one of claims 12,
wherein said machining step is an abrading, grinding or
polishing, dicing, back grinding or wafer polishing step.

20 15. A method for fabricating a semiconductor ingot
comprising the steps of:

discharging, to a waste tank, not only water but also
Si particle generated at a step of machining a crystal ingot
to a wafer, or at a step of machining a semiconductor wafer;

adjusting waste water in said waste water tank to a predetermined density by using a filter device wherein a solid composed of the same material as said Si particle is formed as a second filter on the surface of a first filter;

5 transferring said waste water having said predetermined density to collection means;

 discharging said waste water under pressure;

 using said collection means to generate a block that consists of said Si particle at a predetermined water
10 content and that does not react with a chemical in said waste water tank; and

 using said block consisting of said Si particle as a material to be melted for recycling.

16. A method according to claim 15, wherein said solid
15 is particle dispersed in wastewater.

17. A method according to claim 15 or 16, wherein the surface layer of said second filter is refreshed.

18. A method according to claim 17, wherein, for the refreshment, air bubbles are passed through the surface of
20 said second filter.